

A large industrial facility, possibly a refinery or chemical plant, is shown at night. The structure is complex, with multiple levels of scaffolding, pipes, and large storage tanks. The scene is illuminated by numerous bright lights, creating a high-contrast, blue-toned image. The sky is dark, and the overall atmosphere is industrial and modern.

PRODUCT CATALOGUE

TABLE OF CONTENTS

COMPANY INTRODUCTION	3
----------------------	---

EPOXY RESINS

BASIC EPOXY RESINS	4
---------------------------	---

Epoxy Resins	4
Unmodified Liquid Epoxy Resins	5
Semi-Solid Epoxy Resins	5
Unmodified Solid Epoxy Resins	5
Cycloaliphatic Epoxy Resins	5

MODIFIED EPOXY RESINS	6
------------------------------	---

Modified Liquid Epoxy Resins	6
Modified Solid Epoxy Resins	6
Epoxy Resins – Solution	7
Brominated Epoxy Resins	6
Epoxy Resins for Waterborne Systems	7
Epoxy Resins based on BPA/F	7

HARDENERS	16
------------------	----

REACTIVE DILUENTS	16
--------------------------	----

SPECIALTY EPOXY SYSTEMS

EPOXY SYSTEMS FOR ELECTRO & ELECTRONICS	9
--	---

Insulators, Bushings, Switchgear	9
Instrument & Distribution Transformers	9
Outdoor Applications	9
Prefilled Systems	10
Low Voltage Casting, Encapsulating and Potting	10
Special Casting Systems	10
Adhesives for Electro	10
Pigment Pastes	11
Supplementary Products	11

EPOXY SYSTEMS FOR COMPOSITES	12
-------------------------------------	----

Filament Winding & Pultrusion Systems	12
Hand Lay-up, Infusion & Injection Systems, RTM	12
Prepreg Matrix Systems	13
Adhesives for Composites	13

EPOXY SYSTEMS FOR CONSTRUCTION & FLOORING	14
--	----

Coating Systems	14
------------------------	----

– Impregnation & Primers	
– Industrial Floor Topcoats	
– Transparent Lacquers	

Flooring Systems	14
-------------------------	----

– Decorative Flooring	
– Industrial & Anti-static Floors	
– Binders for Stone Carpet	

Binders for Polymerconcrete & Polymermortar	15
--	----

Adhesives for Construction	15
-----------------------------------	----

SPECIAL ADDITIVES

DECIDOL®	17
----------	----

ALKYD & ROSIN RESINS

Binders for Industrial Coatings	19
Binders for Decorative Coatings	20–21
Binders for Adhesives	21
Binders for Printing Inks	21

HYDROXIDES

Sodium & Potassium Hydroxide	22
------------------------------	----

CHLORINE PRODUCTS & OTHER

Allylchloride	23
Epichlorohydrin	23
Hydrochloric Acid	23
Perchlorethylene	23
Sodium Hypochlorite	23
Triethylamin Trihydrofluoride	23

COMPANY INTRODUCTION

SPOLCHEMIE, a distinguished chemical company based in the Czech Republic, holds a significant position within the European market. With a rich history dating back to 1856, we are recognized as one of the leading manufacturers of synthetic resins in Europe. Our extensive product portfolio includes epoxy resins, specialty epoxy systems, alkyd resins, hydroxides, chlorine derivatives and other chemical products. Our products find wide-ranging applications across various industries among others: automotive, construction, energy, electronics, and pharmaceuticals, underscoring our commitment to innovation, quality and sustainability.

R&D AND INNOVATIONS

Spolchemie's growth has been thrived by focusing on innovative chemical products and technologies that aligns with global trends and customer needs. Our dedicated research teams in Ústí nad Labem collaborate closely with our production and business divisions to swiftly and effectively respond to unique demands.

Our research covers important areas: our resin team works on systems for composites, paints, coatings, and construction, and our inorganics team specializes in chlorine derivatives. Our research institute in Pardubice features state-of-the-art facilities and offers independent certification and analysis through its accredited labs.

The trends in our research and development focus strongly on the utilisation of environmentally friendly and renewable resources, while production focuses on special sophisticated systems of alkyd and epoxy resins..

SUSTAINABILITY CONCEPT

We, at SPOLCHEMIE, believe that systematic and effective prevention and mitigation of harm to the environment and humans together with developing modern and environmentally friendly technologies is key for future sustainable development not only of our company but also of the society as a whole. We feel a responsibility to protect the climate and nature and we respond to demands of our customers who are looking for more sustainable and environmentally friendly solutions. We strive to ensure that our activities are in line with the principles of sustainable development and Responsible Care principles.



BASIC EPOXY RESINS

Our **EnviPOXY®** product range offers significant advantages in terms of quality and environmental benefits. It is the only low molecular epoxy resin produced in Europe **with a maximum renewable content of 33,5% (calculated value)**.

A cradle-to-gate life cycle assessment (LCA) of both epoxy production processes confirmed that the conventional route from propylene has significantly higher environmental impacts. Compared to the propylene route, **the carbon footprint of our environmentally friendly epoxy production from glycerine is lower by 65%**, consumes less energy, and has lower eutrophication and acidification potential.

EnviPOXY®
Resins

FROM FOSSIL TO RENEWABLES

Using our **EnviPOXY®** can contribute to climate protection and reduce environmental impact of your product.



Photo: Epoxy Resin Production Plant - Epistol (2007)

Product	Viscosity (Pa.s, 25 °C)	Epoxy index (mol/kg)	EEW (g/mol)	Hydrolyzable chlorine (%)	Colour (APHA, Gardner*)	Application	Description
---------	----------------------------	-------------------------	----------------	------------------------------	----------------------------	-------------	-------------

EPOXY RESINS – EnviPOXY® | ONLY TOP SELECTED PRODUCTS

EnviPOXY® 520	12,0–14,5	5,21–5,50	182–192	max. 0,03	max.100	Modifications, adhesives, composites	BPA type, low CO₂ footprint
EnviPOXY® 525	10,0–12,0	5,29–5,59	179–189	max. 0,03	max.100	Modifications, adhesives, composites	BPA type, low CO₂ footprint
EnviPOXY® 210 X 75	5,0–12,0	2,0–2,3	445–500		max.1*	High performance 2K coating materials such as anticorrosion primers, baking coatings	75% solution in xylene, low CO₂ footprint
EnviPOXY® 130	0,3–0,6 ²	1,25–1,43	700–800		max.100	Powder coatings	Medium molecular weight "3-type" epoxy resin, low CO₂ footprint

All products are also available as EnviPOXY® – Epoxy Resins with a renewable content up to 33,5%

Product	Viscosity (Pa.s, 25 °C)	Epoxy index (mol/kg)	EEW (g/mol)	Hydrolyzable chlorine (%)	Colour (APHA, Gardner*)	Application	Description
---------	----------------------------	-------------------------	----------------	------------------------------	----------------------------	-------------	-------------

UNMODIFIED LIQUID EPOXY RESINS

CHS-EPOXY® 510	12,5–16,0	5,18–5,46	183–193	max. 0,03	max.200	Modifications, adhesives, composites	BPA type, low tendency to crystallize
CHS-EPOXY® 520	12,0–14,5	5,21–5,50	182–192	max. 0,03	max.100	Modifications, adhesives, composites	BPA type
CHS-EPOXY® 525	10,0–12,0	5,29–5,59	179–189	max. 0,03	max.100	Modifications, adhesives, composites	BPA type
CHS-EPOXY® 525 LA	10,0–12,0	5,30–5,50	182–189	max. 0,03	max.100	Modifications, adhesives, composites	BPA type with low α-glycol content
CHS-EPOXY® 530	8,0–10,0	5,38–5,68	176–186	max. 0,03	max.100	Modifications, adhesives, composites	BPA type
CHS-EPOXY® 590	3,0–5,5	5,70–6,06	165–175	max. 0,03	max.100	Modifications, adhesives, composites	BPF type

SEMI-SOLID EPOXY RESINS

CHS-EPOXY® 301		2,7–3,3	300–370		-	Hot casting, solventborne coatings, prepregs	BPA type semisolid epoxy resin
CHS-EPOXY® 411	0,5–0,8 ¹	3,9–4,2	238–256		max.100	Hot casting, solventborne coatings, prepregs	BPA type semisolid epoxy resin

UNMODIFIED SOLID EPOXY RESINS

CHS-EPOXY® 030	2,6–6 ²	0,25–0,45	2 220–4 000		max.100	Can and coil coatings etc.	High molecular weight "9-type" epoxy resin
CHS-EPOXY® 030 HV	6–8 ²	0,26–0,44	2 273–3 846		max.100	Can and coil coatings etc. with higher viscosity than CHS-EPOXY 030	High molecular weight "9-type" epoxy resin
CHS-EPOXY® 050	1,6–2,6 ²	0,50–0,65	1 550–2 000		max.100	Can and coil coatings etc.	High molecular weight "7-type" epoxy resin
CHS-EPOXY® 070	1,7–2,6 ²	0,61–0,74	1 350–1 640		max.100	Can and coil coatings etc.	High molecular weight "6-type" epoxy resin
CHS-EPOXY® 112	0,5–1,0 ²	0,95–1,11	900–1 050		max.100	Powder coatings	Medium molecular weight "4-type" epoxy resin
CHS-EPOXY® 121	0,4–0,8 ²	1,11–1,25	800–900		max.100	Powder coatings	Medium molecular weight "3, 5-type" epoxy resin
CHS-EPOXY® 130	0,3–0,6 ²	1,25–1,43	700–800		max.100	Powder coatings	Medium molecular weight "3-type" epoxy resin
CHS-EPOXY® 141	0,30–0,55 ²	1,43–1,54	650–700		max.100	Powder coatings	Low molecular weight "2, 5-type" epoxy resin
CHS-EPOXY® 160	0,25–0,45 ²	1,54–1,67	600–650		max.100	Powder coatings	Low molecular weight "2-type" epoxy resin
CHS-EPOXY® 171	0,20–0,35 ²	1,67–1,82	550–600		max.100	Powder coatings, solventborne coatings	Low molecular weight "1, 5-type" epoxy resin
CHS-EPOXY® 211	0,15–0,25 ²	1,82–2,22	450–550		max.100	Solventborne coatings	Low molecular weight "1-type" epoxy resin

CYCLOALIPHATIC EPOXY RESINS

CHS-EPOXY® 560	0,5–1,3	5,50–6,10			max.1*	Outdoor transformers, insulators, bushings etc.	Hexahydrophthalic acid diglycidyl ester
----------------	---------	-----------	--	--	--------	---	---

Product Notes: **1** Viscosity of 70% solution in butylglycol/ 25°C, **2** Viscosity of 40% solution in butylglycol/25°C, **3** In a solution, **4** Recommended mixing ration with filler, **5** Viscosity at 25°C (Brookfield), **6** System (part A:B) has to be mixed with water in the recommended correct ration - see Application Sheet, **7** System (part A:B) can be filled with additional filler in the recommended correct ratio - see Application Sheet, **8** Viscosity (Pa.s, 25°C), **9** Viscosity (Pa.s, 20°C), **10** 50% Xylene solution, **11** In time of loading, **12** Depends on technology used, (pbw) parts by weight.

All products are also available as EnviPOXY® – Epoxy Resins with a renewable content up to 33,5%

MODIFIED EPOXY RESINS

Product	Viscosity (Pa.s, 25 °C)	Epoxy index (mol/kg)	EEW (g/mol)	Hydrolyzable chlorine (%)	Colour (APHA, Gardner*)	Application	Description
---------	----------------------------	-------------------------	----------------	------------------------------	----------------------------	-------------	-------------

MODIFIED LIQUID EPOXY RESINS

CHS-EPOXY® 324	20,0–60,0	3,0–3,4	294–333		max.300	Adhesives for metals, wood, ceramics	Epoxy resin modified with a non-phthalate, non-reactive plasticizer
CHS-EPOXY® 455	2,0–4,0	4,3–4,8	208–232		max.100	Adhesives, civil engineering and composites	Epoxy resin modified with a non-phthalate, non-reactive plasticizer
CHS-EPOXY® 474	0,3–0,6	4,5–4,9	204–223		max.100	Composites, coatings, applications in civil engineering, casting compounds	Epoxy resin modified with mono-functional reactive
CHS-EPOXY® 498	0,5–0,7	4,8–5,1	196–208		max.100	Civil engineering, potting and impregnation	Epoxy resin modified with mono-functional reactive diluent
CHS-EPOXY® 512	2,5–4,1	4,3–4,8	208–233		max.100	Casting, composites, adhesives, construction (bonding agent for mortar, concrete and high chemical resistance compositions)	Epoxy resin modified with non-reactive modifier, flexibilized
CHS-EPOXY® 517	0,55–0,95	4,3–4,7	213–233		max.100	Casting, composites, adhesives, construction (bonding agent for mortar and concrete)	Epoxy resin modified with reactive diluent, flexibilized
CHS-EPOXY® 521	0,6–0,9	4,85–5,1	196–206		max.100	Composites, potting, solventless coatings, civil engineering	Epoxy resin modified with mono-functional reactive diluent
CHS-EPOXY® 531	1,5–2,3	5,5–5,7	175–182		max.100	Composites, solventless coatings and impregnations, construction (bonding agent for mortar, concrete and food industry compositions)	Epoxy resin modified with bi-functional reactive diluent
CHS-EPOXY® 582	0,64–0,72	5,8–6,1	165–173		max.100	Casting, composites, polymer concretes and mortars	Epoxy resin modified with bi-functional reactive diluent
CHS-EPOXY® 619	0,4–0,9	5,9–6,5	155–170	max. 0,2	max.100	High performance laminating, potting, solventless coatings and impregnation	Epoxy resin modified with tri-functional reactive diluent

MODIFIED SOLID EPOXY RESINS

CHS-EPOXY® 112 4F0,5	0,5–1,0 ²	1,05–1,11	900–950			Powder coatings	Modified by 0, 5% of flow control agent
CHS-EPOXY® 112 4F5	0,5–1,0 ²	0,90–1,10	910–1 110			Powder coatings	Modified by 5% of flow control agent
CHS-EPOXY® 130 4F10	0,3–0,6 ²	1,10–1,30	770–910			Powder coatings	Modified by 10% of flow control agent
CHS-EPOXY® 141 4F5	0,35–0,5 ²	1,30–1,45	690–770			Powder coatings	Modified by 5% of flow control agent
CHS-EPOXY® 160 4F2,5	0,25–0,45 ²	1,50–1,70	590–670			Powder coatings	Modified by 2, 5% of flow control agent

BROMINATED EPOXY RESINS


CHS-EPOXY® B 200 M 80	1,1–2,3	1,8–2,3	435–556	max. 0,1	max.1*	Prepregs for printed circuits boards, laminates	80% solution of brominated (21% wt.) medium molecular weight epoxy resin, dissolved in methyl ethyl ketone
CHS-EPOXY® B 201 M 80	1,5–2,0	2,3–2,5	400–435	max. 0,1	max.1*	Prepregs for printed circuits boards, laminates, UV blocking	80% solution of brominated (21% wt.) medium molecular weight epoxy resin, dissolved in methyl ethyl ketone

All products are also available as EnviPOXY® – Epoxy Resins with a renewable content up to 33,5%

EPOXY RESINS - SOLUTION

CHS-EPOXY® 101 X 60	2,5–5,0				max. 5*	Air-drying coatings, in the mixture with melamine- formaldehyde resins for the formulation of baking coatings	Fast air drying 60% solution of epoxy ester
CHS-EPOXY® 200 M 75	0–2,0	1,9–2,3	435–525	max. 0,015	max. 1*	Production of prepreges	Solution in methylethylketone
CHS-EPOXY® 200 M 80	2,5–5,5	2,0–2,4	410–500	max. 0,015	max. 1*	Production of prepreges	Solution in methylethylketone
CHS-EPOXY® 210 X 75	5,0–12,0	2,0–2,3	445–500		max. 1*	High performance 2K coating materials such as anticorrosion primers, baking coatings	75% solution in xylene
CHS-EPOXY® 222 IX 60	0,2–0,4	1,8–2,3	430–555		max. 3*	Anticorrosive paint in marine and railway industry, gas industry, insulation of building, sewage pipes and reservoirs	60% solution in solvent blend, flexibilized
CHS-EPOXY® 301 X 80	5,5–7,5	2,7–3,3	300–370		max. 1*	High solid coatings, anticorrosion primers, baking lacquers, treatment of metal surfaces	80% xylene solution of BPA based semisolid epoxy resin
CHS-EPOXY® 411 X 80	0,6–0,8	3,9–4,2	238–256		max. 100	High solid coatings, anticorrosion primers, baking lacquers	80% xylene solution of BPA based semisolid epoxy resin
CHS-EPOXY® 520 M 80	0,04–0,05	4,1–4,4 ³	227–244 ³		max. 300	High solid coatings, prepregs etc.	80% solution in methylethylketone

EPOXY RESINS FOR WATERBORNE SYSTEMS

 CHS-EPOXY® 160 V 55	0,1–1,0	1,25–1,80	555–800			Varnish and binder of paints for wood, wood fibre boards, concrete, metals and other materials	Water dispersion of a medium molecular weight epoxy resin
 CHS-EPOXY® 200 V 55	0,1–0,7	1,88–2,22	455–525			Varnish and binder of paints for wood, wood fibre boards, concrete, metals and other materials	Water dispersion of a low molecular weight epoxy resin

EPOXY RESINS BASED ON BPA/F

CHS-EPOXY® 501	0,6–0,8	5,0–5,3	188–200	max. 0,1	max. 100	Composites, high solid, anticorrosion paints, civil engineering, casting	BPA/F resin modified by monofunctional reactive diluent
CHS-EPOXY® 514	0,8–1,1	5,1–5,4	185–196	max. 0,1	max. 100	Composites, high solid, anticorrosion paints, civil engineering, casting	BPA/F resin modified by monofunctional reactive diluent
CHS-EPOXY® 571	6,0–8,0	5,4–5,7	175–185	max. 0,03	max. 100	Coatings, penetrants, filled systems, casting applications and insulating materials	BPA/F epoxy resin
CHS-EPOXY® 572	4,5–7,0	5,5–5,8	172–182	max. 0,03	max. 100	Coatings, penetrants, filled systems, casting applications and insulating materials	BPA/F epoxy resin
CHS-EPOXY® 573	8,0–10,5	5,3–5,6	179–189	max. 0,03	max. 100	Coatings, penetrants, filled systems, casting applications and insulating materials	BPA/F epoxy resin
CHS-EPOXY® 574	1,4–1,7	5,5–5,75	174–182	max. 0,1	max. 100	Composites, civil and electrical engineering, high-solid coatings	BPA/F resin modified by difunctional reactive diluent
CHS-EPOXY® 575	0,7–0,9	5,6–5,9	169–179	max. 0,1	max. 100	Solventless coatings, penetrants, filled systems, casting applications and insulating materials, high solid coatings	BPA/F resin modified by difunctional reactive diluent

 waterborne

Product Notes: **1** Viscosity of 70% solution in butylglycol/ 25°C, **2** Viscosity of 40% solution in butylglycol/25°C, **3** In a solution, **4** Recommended mixing ration with filler, **5** Viscosity at 25°C (Brookfield), **6** System (part A:B) has to be mixed with water in the recommended correct ration - see Application Sheet, **7** System (part A:B) can be filled with additional filler in the recommended correct ratio - see Application Sheet, **8** Viscosity (Pa.s, 25°C), **9** Viscosity (Pa.s, 20°C), **10** 50% Xylene solution, **11** In time of loading, **12** Depends on technology used, (pbw) parts by weight.

All products are also available as EnviPOXY® – Epoxy Resins with a renewable content up to 33,5%

SPECIALTY EPOXY SYSTEMS

Our Specialty Epoxy Systems portfolio covers these applications:

- Electro & Electronics
- Composites
- Construction & Flooring

EnviPOXY®
Systems

FROM
FOSSIL TO
RENEWABLES

EnviPOXY® Systems are based on the liquid EnviPOXY® Resin containing the maximum renewable content of 33,5 %*.

Thanks to the experts in our R&D centers, we are ready to develop top performance products with **high renewable content** that address customer-specific needs.

*calculated value



SPECIALTY EPOXY RESIN SYSTEMS

Product	Components	Mixing ratio (pbw)	Tg, DSC (°C)	Viscosity (mPa.s)	Pot-life	Description
---------	------------	--------------------	--------------	-------------------	----------	-------------

NEW INSULATORS, BUSHINGS, SWITCHGEAR

CHS-EPODUR® Envi 520-1787	A/B/C1/D1	100/90/0,5/5/360 ⁴	105–115	5 000/60 °C	1–2 h/80 °C	Epoxy resin and special hardener with low tendency to crystallize. Preferred for high and medium voltage applications.
CHS-EPODUR® Envi 494-1667	A/B/C2/D2	100/85/0,8/4/405 ⁴	100–115	25 000/45 °C 8 000/60 °C	2 h/60 °C	Modified epoxy resin and hardener system suitable for high and medium voltage applications.
CHS-EPODUR® Envi 494-1667	A/B/C2	100/77,5/0,8/345 ⁴	110–125	18 000/45 °C 7 000/60 °C	2 h/60 °C	Modified epoxy resin and hardener system suitable for high and medium voltage applications.
CHS-EPODUR® Envi 467-1637	A/B	100/75/345 ⁴	105–115	6 000/60 °C	2 h/60 °C	Modified epoxy resin and hardener system suitable for high and medium voltage applications. "REACH free".
CHS-EPODUR® Envi 466-1667	A/B/C2	100/80/0,6/370 ⁴	105–115	7 000/60 °C	3 h/60 °C	Modified epoxy resin and special hardener with low tendency to crystallize. System with very good toughness.
CHS-EPODUR® Envi 466-1667	A/B/C2	100/80/0,6/370 ⁴	105–115	7 000/60 °C	3 h/60 °C	Modified epoxy resin and hardener system suitable for high and medium voltage applications.

NEW INSTRUMENT & DISTRIBUTION TRANSFORMERS

CHS-EPODUR® Envi 520-1787	A/B/C1/D1	100/85/0,5/15/370 ⁴	75–85	5 000/60 °C	1–2 h/80 °C	Epoxy resin and special hardener with low tendency to crystallize. System with very good toughness.
CHS-EPODUR® Envi 531-1787	A/B/C1/D1	100/85/0,5/10/370 ⁴	70–85	20 000/45 °C 8 500/60 °C	1–2 h/80 °C	Modified epoxy resin and special hardener with low tendency to crystallize. System with very good toughness and higher degree of filling.
CHS-EPODUR® Envi 494-1667	A/B/C2/D4	100/85/0,6/17/385 ⁴	60–75	4 000/60 °C	1–2 h/80 °C	Modified resin and hardener system. High degree of filling.
CHS-EPODUR® Envi 494-1718	A/B/D1	100/77/5/340 ⁴	85–95	18 000/45 °C 7 000/60 °C	1–2 h/80 °C	Modified epoxy resin and special hardener with low tendency to crystallize. System with very good toughness.
CHS-EPODUR® Envi 464-1657	A/B	100/75/389 ⁴	80–90	20 000/45 °C 8 500/60 °C	1–2 h/80 °C	Modified resin and hardener system. High degree of filling.
CHS-EPODUR® Envi 494-1737	A/B	100/81/280 ⁴	90-105	3 500/60 °C	2 h/80 °C	Modified epoxy resin and special hardener with low tendency to crystallize. System with very good toughness and longer pot-life.

NEW PREFILLED SYSTEMS

SADURIT® Envi 520-1988	A/B	100/100	110–125	3 500/60 °C	8 h/40 °C; 2–3 h/60 °C	Excellent crack resistance at low temperatures, good toughness. UL 94 HB. High Tg.
SADURIT® Envi 520-1987	A/B	100/100	120–130	4 000/60 °C	6 h/40 °C; 1–2 h/60 °C	UL 94 V0. High Tg.
SADURIT® Envi 494-1667	A/B	100/85	60–70	4 000/60 °C	6 h/40 °C; 2–3 h/60 °C	Excellent crack resistance at low temperatures, good toughness. UL 94 HB.
SADURIT® Envi 560-1987	A/B	100/100	80–90	5 000/60 °C	6 h/40 °C; 1–2 h/60 °C	Cycloaliphatic resin for outdoor application. Excellent crack resistance at low temperatures, good toughness. UL 94 HB.

Product Notes: **1** Viscosity of 70% solution in butylglycol/ 25°C, **2** Viscosity of 40% solution in butylglycol/25°C, **3** In a solution, **4** Recommended mixing ration with filler, **5** Viscosity at 25°C (Brookfield), **6** System (part A:B) has to be mixed with water in the recommended correct ration - see Application Sheet, **7** System (part A:B) can be filled with additional filler in the recommended correct ratio - see Application Sheet, **8** Viscosity (Pa.s, 25°C), **9** Viscosity (Pa.s, 20°C), **10** 50% Xylene solution, **11** In time of loading, **12** Depends on technology used, (pbw) parts by weight.

CHS-EPODUR® Envi and SADURIT® Envi are based on EnviPOXY® Resin with a maximum renewable content of 33.5 %.

Product	Components	Mixing ratio (pbw)	Tg, DSC (°C)	Viscosity (mPa.s)	Pot-life	Description
---------	------------	--------------------	--------------	-------------------	----------	-------------

NEW LOW VOLTAGE CASTING, ENCAPSULATING AND POTTING

SADURIT® Envi 531-0522	A / B	100 / 13	100–110	6 000 / 25 °C	2 h/25 °C/1 000 g	Room temperature cured modified resin system, long potlife. 2K with prefilled component A.
------------------------	-------	----------	---------	---------------	-------------------	--

NEW SPECIAL CASTING SYSTEMS

VEROPAL 520-1987	A / B	100 / 220	95–110	4 000 / 25 °C; 400 / 60 °C	4 h/60 °C	Prefilled – 2K system with prefilled hardener. Low viscosity system.
VEROPAL 520-1668	A / B	100 / 220	95–110	4 000 / 25 °C; 400 / 60 °C	4 h/60 °C	Prefilled – 2K system with prefilled hardener. Low viscosity system. Excellent crack resistance.
CHS-EPODUR® Envi 520-1997	A / B / C3	100 / 95 / 0,5 / 350 ⁴	165–175	5 000 / 60 °C	4 h/60 °C	Epoxy resin and special hardener with high Tg.

Product	Components	Mixing ratio (pbw)	Tg, DSC (°C)	Viscosity (mPa.s)	Pot-life	Description
---------	------------	--------------------	--------------	-------------------	----------	-------------

OUTDOOR APPLICATIONS

CHS-EPODUR® 560-1987	A / B / C1	100 / 90 / 0,5 / 360 ⁴	90–100	5 000 / 60 °C	1–2 h/60 °C	Cycloaliphatic resin and modified hardener system with very good UV resistance.
CHS-EPODUR® 560-1987	A / B / C1 / D1	100 / 90 / 0,5 / 10 / 370 ⁴	80–90	5 000 / 60 °C	1–2 h/60 °C	Cycloaliphatic resin and modified hardener system with very good UV resistance. Improved toughness.
CHS-EPODUR® 560-1787	A / B / C2	100 / 90 / 0,4 / 375 ⁴	80–90	5 000 / 60 °C	1–2 h/60 °C	Cycloaliphatic resin and modified hardener system with very good UV resistance. Excellent toughness.
CHS-EPODUR® 560-1577	A / B / C2	100 / 90 / 0,5 / 370 ⁴	105–115	6 000 / 60 °C	2 h/60 °C	Cycloaliphatic resin and hardener system with very good UV resistance. High Tg.
NEW CHS-EPODUR® 504-1577	A / B / C2 / D5	100 / 82 / 0,5 / 10 / 371 ⁴	75–95	2 500 / 60 °C	2 h/60 °C	Hydrophobic cycloaliphatic resin and hardener system with very good UV resistance.
NEW CHS-EPODUR® 561-1577	A / B / C2 / D5	100 / 90 / 0,5 / 10 / 390 ⁴	100–120	4 000 / 60 °C	2 h/60 °C	Hydrophobic cycloaliphatic resin and hardener system with very good UV resistance. High Tg.

Product	Components	Mixing ratio (pbw)	Tg, DSC (°C)	Gel Time (10g/50g min)	Description
---------	------------	--------------------	--------------	------------------------	-------------

SUPPLEMENTARY PRODUCTS

NEW VEROPAL RA 100 LV					Solvent-free release agent for epoxy and polyurethane materials. Stable up to 300 °C.
VEROPAL 520-T17M	A / B	100 / 17	90–110	10–20 / 5–10	Repairing epoxy system for indoor applications. Component A with common filler and component B without filler.
VEROPAL 560-T17M	A / B	100 / 14	80–95	10–20 / 5–10	Repairing epoxy system for indoor applications. Component A with wollastonite filler and component B without filler.
VEROPAL T520-T17M	A / B	100 / 34	90–110	10–20 / 5–10	Fixation thixotropic epoxy system for indoor applications. Component A and B without filler.

Product Notes: **1** Viscosity of 70% solution in butylglycol/ 25°C, **2** Viscosity of 40% solution in butylglycol/25°C, **3** In a solution, **4** Recommended mixing ration with filler, **5** Viscosity at 25°C (Brookfield), **6** System (part A:B) has to be mixed with water in the recommended correct ration - see Application Sheet, **7** System (part A:B) can be filled with additional filler in the recommended correct ratio - see Application Sheet, **8** Viscosity (Pa.s, 25°C), **9** Viscosity (Pa.s, 20°C), **10** 50% Xylene solution, **11** In time of loading, **12** Depends on technology used, (pbw) parts by weight.

CHS-EPODUR® Envi and SADURIT® Envi are based on EnviPOXY® Resin with a maximum renewable content of 33.5 %.

Product	RAL	Colour
---------	-----	--------

PIGMENT PASTES – INDOOR

E-pasta BF 135M-BA	RAL3013	Tomato red
E-pasta BF 160M-BA	RAL3011	Brown red
E-pasta BF 661-BA	RAL8016	Mahogany Brown
E-pasta BF 662LV-BA	RAL8016	Mahogany Brown, low viscosity
E-pasta BF 645T LV-BA	RAL8016	Mahogany Brown, thermal stability
E-pasta BF 318-BA	RAL9011	Graphite black
E-pasta FW 200-BA	RAL9017	Traffic black
E-pasta KRBF 2478-BA	RAL7024	Graphite grey
E-pasta MIX 7032-BA	RAL7032	Pebble grey
E-pasta HB 550-BA	RAL5005	Signal blue
E-pasta LG 5G-BA	RAL6032	Signal green
E-pasta GN-M-BA	RAL6025	Fern green
E-pasta BFO 130M-BA	RAL2003	Pastel Orange
E-pasta PY 6615-BA	RAL1016	Sulphur yellow

Product	RAL	Colour
---------	-----	--------

PIGMENT PASTES – INDOOR

E-pasta BF 1135M-OD	RAL3013	Tomato red
E-pasta BF 1660-OD	RAL8016	Mahogany Brown
E-pasta BF 1318-OD	RAL9011	Graphite black
E-pasta KRBF 4478-OD	RAL7024	Graphite grey
E pasta MIX 7035-OD	RAL7035	Light grey

Product	Mixing ratio (pbw)	Tg, DSC (°C)	Pot-life	Shear strength (MPa)	Description
---------	--------------------	--------------	----------	----------------------	-------------

ADHESIVES

VEROBOND® 520-2608	100 / 140	70–80	20 min/25 °C/50g	20–25	Structural adhesive with high elongation up to 55% and with excellent peel and shear strength.
VEROBOND® QUICK	100 / 100	50–60	3 min/25 °C/10g	10–12	Unique, very fast epoxy adhesive (5 minutes curing time).
VEROBOND® SUPER	100 / 100	70–80	20 min/25 °C/10g	20–24	2K epoxy structural adhesive with high elongation up to 55% and excellent mechanical properties – peel strength and shear strength. Prefilled.
VEROBOND® 14	100 / 50	80–85	60 min/25 °C/100g	20–24	Epoxy thixotropic adhesive or casting systems, cured at room temperature. System with high strength with good chemical resistance. Prefilled.
VEROBOND® 15	100 / 100	60–70	25 min/25 °C/100g	20–24	Unique hybrid epoxy 2K structural adhesive with high elongation and excellent mechanical properties – peel strength and shear strength. Prefilled.

Product Notes: **1** Viscosity of 70% solution in butylglycol/ 25°C, **2** Viscosity of 40% solution in butylglycol/25°C, **3** In a solution, **4** Recommended mixing ration with filler, **5** Viscosity at 25°C (Brookfield), **6** System (part A:B) has to be mixed with water in the recommended correct ration - see Application Sheet, **7** System (part A:B) can be filled with additional filler in the recommended correct ratio - see Application Sheet, **8** Viscosity (Pa.s, 25°C), **9** Viscosity (Pa.s, 20°C), **10** 50% Xylene solution, **11** In time of loading, **12** Depends on technology used, (pbw) parts by weight.

EPOXY RESIN SYSTEMS FOR COMPOSITES

Product	Components	Mixing ratio (pbw)	Tg, DSC (°C)	Viscosity (mPa.s)	Pot-life	Description
---------	------------	--------------------	--------------	-------------------	----------	-------------

FILAMENT WINDING & PULTRUSION SYSTEMS

CHS-EPODUR® 494-1667	A/B/C2	100/85/1	115–125	500–1 000 ⁵	> 10 h/25 °C	Medium viscosity. Curing at higher temperature (at least 80 °C)
CHS-EPODUR® 520-1687	A/B/C2	100/90/1	130–145	500–1 000 ⁵	> 10 h/25 °C	Long pot life, medium viscosity. Curing at higher temperature (at least 80 °C)
CHS-EPODUR® 520-1667	A/B/C2	100/85/1	115–130	500–1 000 ⁵	> 10 h/25 °C	Medium viscosity. Curing at higher temperature (at least 80 °C)
CHS-EPODUR® 520-1997	A/B/C3	100/95/1	165–175	1 000–1 200 ⁵	> 10 h/25 °C	High thermal resistance. Post curing above 160 °C
CHS-EPODUR® 520-1787	A/B/C1/D1	100/85/0,5/10	85–95	1 500–2 000 ⁵	> 10 h/25 °C	High mechanical properties, long pot life. Curing at higher temperature (at least 80 °C)
CHS-EPODUR® 574-0522	A/B	100/30	85–100	200–500 ⁵	1–2 h/25 °C	Curing at ambient temperature, slow reactivity

HAND LAY-UP, INFUSION & INJECTION SYSTEMS, RTM

CHS-EPODUR® 582-0512/0492/0502/0482/0590	A/B	100/30	90–115	200–400 ⁵	0,3–4 h/25 °C	Combination of one resin with five hardeners, low viscosity, fast to slow reactivity. Optimal for infusion
CHS-EPODUR® 574-0512/0492/0502/0482/0590	A/B	100/28	90–115	350–650 ⁵	0,3–4 h/25 °C	Combination of one resin with five hardeners, medium viscosity, fast to slow reactivity. Optimal for hand lay-up
CHS-EPODUR® 581-0542/0562	A/B	100/32	80–85	200–250 ⁵	1–2 h/25 °C	Combination of one resin with two hardeners, low viscosity, fast to slow reactivity. Optimal for wind mill blades
CHS-EPODUR® 582-0600	A/B	100/37	130–150	350–550 ⁵	2–3 h/25 °C	Slow reactivity, low viscosity, high mechanical properties
CHS-EPODUR® 582-0420	A/B	100/25	120–130	300–450 ⁵	0,5–1 h/25 °C	Medium reactivity, low viscosity, high mechanical properties
CHS-EPODUR® 619-0600	A/B	100/40	115–130	200–500 ⁵	2–3 h/25 °C	Slow reactivity, high mechanical properties. Optimal for hand lay-up
CHS-EPODUR® 619-0492	A/B	100/32	80–90	200–500 ⁵	12–30 min/25 °C	Medium reactivity, high mechanical properties. Optimal for hand lay-up
CHS-EPODUR® 621-0600	A/B	100/40	115–130	500–800 ⁵	0,5–1 h/25 °C	Slow reactivity, high mechanical properties. Optimal for hand lay-up
CHS-EPODUR® 621-0492	A/B	100/32	85–100	300–500 ⁵	20–40 min/25 °C	Medium reactivity, high mechanical properties. Optimal for hand lay-up
CHS-EPODUR® 520-1787	A/B/C1/D1	100/85/0.5/10	85–95	1 500–2 000 ⁵	> 10 h/25 °C	High mechanical properties, long pot life. Curing at higher temperature (at least 80 °C)
CHS-EPODUR® 520-1687	A/B/C2	100/90/1	130–145	5 500–1 000 ⁵	> 10 h/25 °C	Long pot life, low viscosity. Curing at higher temperature (at least 80 °C)
CHS-EPODUR® 520-1667	A/B/C2	100/85/1	115–130	500–1 000 ⁵	> 10 h/25 °C	Low viscosity. Curing at higher temperature (at least 80 °C)
CHS-EPODUR® 520-1997	A/B/C3	100/95/1	165–175	1 000–1 200 ⁵	> 10 h/25 °C	High thermal resistance. Post curing above 160 °C
CHS-EPODUR® 574-0904	A/B	100/50	70–80	1 600–2 200 ⁵	12-15 min/25 °C	Laminated system with medium viscosity. High adhesion to dural, steel and other metal surfaces.

All products are also available as EnviPOXY® – Epoxy Resins with a renewable content up to 33,5%

Product	Components	Mixing ratio (pbw)	Tg, DSC (°C)	Viscosity (mPa.s)	Pot-life	Description
---------	------------	--------------------	--------------	-------------------	----------	-------------

PREPREG MATRIX SYSTEMS

	CHS-EPODUR® 525-0269	A / B / C55	100 / 12 / 0-3	115-135	14 000 / 23 °C 1 500 / 40 °C	2-8 h / 25 °C ¹²	Solvent-free epoxy prepregging system with chemically induced B-stage, adjustable tack/ drapability. For cold, simple equipped processing. Recommended for general industrial and sport & leisure applications.
NEW	CHS-EPODUR® 411-0269	A / B / C55	100 / 9 / 0-2	120-128	9 800 / 55 °C 2 700 / 70 °C	0,5-2 h / 25 °C ¹²	Solvent-free epoxy system for hot-melt prepregging, adjustable tack. For industrial and sport & leisure composite applications.
NEW	CHS-EPODUR® N 554-0249	A / B / C55	100 / 10 / 0-3	120-165	10 000 / 40 °C 2 000 / 55 °C	1-4 h / 25 °C ¹²	Solvent-free epoxy system for hot-melt prepregging, adjustable tack/drapability. For applications with higher temperature resistance.

Product	Components	Mixing ratio (pbw)	Tg, DSC (°C)	Shear strength (MPa)	Pot-life	Description
---------	------------	--------------------	--------------	----------------------	----------	-------------

ADHESIVES FOR COMPOSITEST

	VEROBOND® QUICK	A / B	100 / 100	50-60	10-12	3 min/25 °C/10g	Unique, very fast epoxy adhesive (5 minutes curing time)
	VEROBOND® 520-2608	A / B	100 / 100	70-80	20-25	20 min/25 °C/50g	Structural adhesive with high elongation up to 55% with excellent peel and shear strength
	VEROBOND® SUPER	A / B	100 / 50	80-85	20-24	20 min/25 °C/10g	Structural adhesive with high elongation up to 55% with excellent peel and shear strength
	VEROBOND® 14	A / B	100 / 100	60-70	20-24	60 min/25 °C/100g	Epoxy adhesive cured at room temperature. Systems is a thixotropic paste of high strength with good chemical resistance
	VEROBOND® 15	A / B	100 / 140	70-80	20-24	25 min/25 °C/100g	Hybrid epoxy structural adhesive with high elongation and excellent peel and shear strengths
	VEROBOND® 531-0903	A / B	100 / 50	50-60	15-20	35 min/25 °C/400g	Epoxy adhesive with low viscosity, cured at room temperature. Optimal for chemical anchors
	VEROBOND® 521-0846	A / B	100 / 50	60-70	6-8	28 min/25 °C/15g	2K epoxy structural adhesive. It is used for structural bonding of a wide range of substrates, especially metals, metal structures, wood and ceramics

Product Notes: **1** Viscosity of 70% solution in butylglycol/ 25°C, **2** Viscosity of 40% solution in butylglycol/25°C, **3** In a solution, **4** Recommended mixing ration with filler, **5** Viscosity at 25°C (Brookfield), **6** System (part A:B) has to be mixed with water in the recommended correct ration - see Application Sheet, **7** System (part A:B) can be filled with additional filler in the recommended correct ratio - see Application Sheet, **8** Viscosity (Pa.s, 25°C), **9** Viscosity (Pa.s, 20°C), **10** 50% Xylene solution, **11** In time of loading, **12** Depends on technology used, (pbw) parts by weight.



All products are also available as EnviPOXY® – Epoxy Resins with a renewable content up to 33,5%

EPOXY RESIN SYSTEMS FOR CONSTRUCTION & FLOORING



Product	Components	Mixing ratio (pbw)	Application	Description
---------	------------	--------------------	-------------	-------------

COATING SYSTEMS



IMPREGNATION & PRIMERS

	EPOSTYL® 200 V	A/B	100/26 ⁶	Primer/penetrating sealer	Waterborne epoxy dispersion
	CHS-EPOSTYL® 521-2433	A/B	100/120 ⁶	Primer/penetrating sealer	Solvent-free water-based epoxy system
	CHS-EPODUR® 474 PRIMER	A/B	100/23	Bonding agent, primer for bridges, roads, pavements, flooring	Low viscosity epoxy system, penetration, adhesion and water control insulation
NEW	CHS-EPODUR® 474 PRIMER FAST	A/B	100/40	Bonding agent, primer	Low viscosity epoxy system, for use at lower temperature
NEW	SADURIT® 474 PRIMER	A/B	100/14	Prefilled penetration coating for concrete substrates	Prefilled epoxy system

INDUSTRIAL FLOOR TOPCOATS

	SADURIT® Z 1	A/B	100/25	Coloured coating systems, high mechanical & chemical resistance, interior/exterior	Solvent based epoxy system. Different colours upon request (based on RAL).
	EPOSTYL® 215 V	A/B	100/14 ⁶	Matt topcoat system for concrete, useable in poorly ventilated rooms, vapour permeable	Waterborne epoxy system. Different colours upon request (based on RAL).
	EPOSTYL® 521-01	A/B	100/30	Coloured coating system with higher UV resistance	Solvent-free epoxy system. Different colours upon request (based on RAL).
	EPOSTYL® 200 V MAT	A/B	100/21 ⁶	Matt top coat for flooring, parquets and other surfaces	Waterborne matt coating

TRANSPARENT LACQUERS

	EPOSTYL® 200 V	A/B	100/26 ⁶	Glossy topcoat for interior applications on wood, concrete and metal	Waterborne epoxy dispersion
	EPOSTYL® 200 V MAT	A/B	101/21 ⁶	Matt topcoat for flooring, parquets and other surfaces	Waterborne matt coating

FLOORING SYSTEMS

DECORATIVE FLOORING

	EPOSTYL® 521-01	A/B	100/30	Universal pigmented epoxy self-levelling flooring system	Solvent-free epoxy system. Different colours upon request (based on RAL).
	EPOSTYL® GRANIT	A/B/C	70/30/150	High decorative epoxy self-levelling flooring system-granite design	Solvent-free epoxy system, excellent appearance

INDUSTRIAL & ANTI-STATIC FLOORS

	EPOSTYL® 521-01	A/B	100/30	Universal pigmented epoxy self-levelling flooring system	Solvent-free epoxy system. Different colours upon request (based on RAL).
	EPOSTYL® 521-01 AS	A/B	100/30	Pigmented self-levelling flooring system, chemically resistant and antistatic. Suitable for interior.	Solvent-free epoxy system
	EPOSTYL® 521 FLEX	A/B	100/72	Self-levelling and gravelled flooring and coatings for covering of cracks, for garages and interiors	Natural rubber epoxy system with excellent ductility above 70% and stretch resistance

BINDERS FOR STONE CARPET

	CHS-EPODUR® STONE	A/B	100/43 ⁷	Pavements, flooring	Special epoxy system for stone carpets
	CHS-EPODUR® STONE UV	A/B	100/43 ⁷	Pavements, flooring	Special epoxy system for stone carpets, improved UV stability
	CHS-EPODUR® STONE GEL	A/B	100/40	Stone carpet finishing gel	Special thixotropic epoxy system for finishing stone carpet

Product	Hardener	Components	Mixing ratio (pbw)	Application	Description
---------	----------	------------	--------------------	-------------	-------------

BINDERS FOR POLYMERCONCRETE & POLYMERMORTAR

CHS-EPOXY® 455	TELALIT® 0240		100/10 ⁷	Binder for polymer mortars and concretes, adhesives	Solvent-free epoxy system with high chemical resistance
	TELALIT® 0492		100/23 ⁷	Binder for polymer mortars and concretes, coatings, chemical anchors	Solvent-free epoxy system, accelerated, excellent mechanical properties
	TELALIT® 0846		100/39 ⁷	Binder for polymer mortars and concretes, adhesives	Solvent-free epoxy system with high chemical resistance
CHS-EPOXY® 474	TELALIT® 0846		100/40 ⁷	Binder for polymer mortars and concretes, coatings, chemical anchors	Solvent-free epoxy system, accelerated, excellent mechanical properties, very fast hardening
	TELALIT® 0492		100/23 ⁷	Chemical anchors, polymer concretes and mortars	Special solvent-free epoxy system, low temperature, wet condition, very fast hardening
CHS-EPOXY® 512	TELALIT® 0240		100/10 ⁷	Very fast curing time in low temperature, fast sandability	Standard epoxy system, low temperature, wet conditions
	TELALIT® 0846		100/39 ⁷	Penetration with interlayer, adhesive bridge	Standard epoxy system, wet conditions, very fast hardening
CHS-EPOXY® 517	TELALIT® 0240		100/11 ⁷	Binder for polymer mortars and concretes, adhesives	Solvent-free epoxy system with high chemical resistance
	TELALIT® 0846		100/44 ⁷	Chemical anchors, polymer concretes and mortars	Special solvent-free epoxy system, low temperature, wet condition, very fast hardening
CHS-EPOXY® 531	TELALIT® 0240		100/12 ⁷	Binder for polymer mortars and concretes	Solvent-free system with high chemical resistance
	TELALIT® 0846		100/47 ⁷	Very fast curing in standard temperature, using in low temperature, fast sandability	Solvent-free system, low temperature, wet conditions, very fast hardening

ADHESIVES FOR CONSTRUCTION

CHS-EPOXY® 512	TELALIT® 0240		100/10	For standard temperatures & higher chemical resistance	Epoxy bonding agent for fixing of metal parts into mortar constructions
CHS-EPOXY® 324	TELALIT® 0240		100/7	For standard temperatures, good chemical resistance	Special phthalate-free epoxy system for adhesive composition and construction sealant
CHS-EPOXY® 324	TELALIT® 0343		100/11	Adhesive for metal, wood, glass	Standard system, higher viscosity, balanced shear and peel strenght, resistant up to 60 °C
VEROBOND® 520-2608		A/B	100/140	Universal adhesive for various type of materials, including thermo-plastics and composites	High toughness, excellent peel strenght, resistance up to 95 °C
VEROBOND® 531-0903		A/B	100/50	Optimal for chemical anchors	Epoxy adhesive with low viscosity, cured at room temperature
VEROBOND® QUICK		A/B	100/100	Universal adhesive for various type of materials	Unique, very fast epoxy adhesive (5 minutes curing time)
VEROBOND® SUPER		A/B	100/100	Universal adhesive for various type of materials, including thermo-plastics and composites	Adhesive with excellent shear and peel strenght, resistant up to 85 °C
VEROBOND® 14		A/B	100/50	Adhesive for various type of materials	Epoxy adhesive or casting systems, cured at room temperature. Systems is a thixotropic paste adhesive of high strength with good chemical resistance
VEROBOND® 15		A/B	100/100	Adhesive for various type of materials	Hybrid epoxy structural adhesive with high elongation and excellent peel and shear strenghts

Product Notes: **1** Viscosity of 70% solution in butylglycol/ 25°C, **2** Viscosity of 40% solution in butylglycol/25°C, **3** In a solution, **4** Recommended mixing ration with filler, **5** Viscosity at 25°C (Brookfield), **6** System (part A:B) has to be mixed with water in the recommended correct ration - see Application Sheet, **7** System (part A:B) can be filled with additional filler in the recommended correct ratio - see Application Sheet, **8** Viscosity (Pa.s, 25°C), **9** Viscosity (Pa.s, 20°C), **10** 50% Xylene solution, **11** In time of loading, **12** Depends on technology used, (pbw) parts by weight.

All products are also available as EnviPOXY® – Epoxy Resins with a renewable content up to 33,5%

HARDENERS

	Product	Viscosity (mPa.s, 25 °C)	Amine number (mg KOH/g)	HEW (g/mol)	Application	Description
NEW	TELALIT® 0240	5–50		24	Standard, civil engineering, composites, adhesives	Aliphatic amine, substitution of CHS-HARDENER P 11
	TELALIT® 0420	10–25	600–650	42	Composites, higher Tg	Cycloaliphatic amine
	TELALIT® 0430	5–50	1 250–1 320	43	Composites, civil engineering, faster curing, higher toughness	Cycloaliphatic amine
	TELALIT® 0492	15–30	550–600	49	Composites, civil engineering	Cycloaliphatic modified
	TELALIT® 0500	5–50	1 100–1 200	50	Composites, accelerated	Cycloaliphatic amine
	TELALIT® 0590	5–10	440–490	59	Composites, long pot life	Polyoxyetheramine
	TELALIT® 0600	80–120	450–500	62	High performance composites, long pot life, highest Tg	Cycloaliphatic, modified
	TELALIT® 0842	1 100–1 900	min.290	84	Hardening in wet conditions, applicable in different weather conditions	Solvent-free system, under water curing
	TELALIT® 0846	550–750	345–375	84	Universal hardener for epoxy systems, applicable in lower temperatures, unsuitable for food, beverages and drinking water	Mannich base without phenol, substitution of TELALIT® 60
	TELALIT® 0903	200–500	320–350	90	Self-levelling flooring, nonylphenol free, low yellowing	Cycloaliphatic adduct modified
	TELALIT® 1040	10–30	230–260	104	Waterborne coatings, high solid coatings, nonylphenol free	Polyoxyetheramine
	TELALIT® 1203 NF	50–400	250–300	120	For high solid coatings, nonyl phenol free	Cycloaliphatic adduct, modified
NEW	TELALIT® 3509 IX 50	200–700	110–135	350	Lacquers, anticorrosive coatings	Aliphatic adduct modified, substitution of TELALIT 160
NEW	TELALIT® 2433 VBG 50	1 000–2 000	130–150	243	Waterborne systems	Polyamine adduct modified, substitution of TELALIT 180
	TELALIT® 2608	5 000–7 000	95–115	260	High performance super toughness adhesives	Aliphatic and cycloaliphatic based modified
	TELALIT® 3404 X 70	700–2 000	145–165	340	Anticorrosive coatings, nonylphenol free	Polyamide
	TELALIT® 0343	400–1 200	850–1 200	34	Composites, civil engineering	Aliphatic adduct
	TELALIT® 95	170–400	300–500	95	Self-levelling flooring	Cycloaliphatic adduct modified

REACTIVE DILUENTS

	Product	Viscosity (mPa.s, 25 °C)	EPOXY index (mol/kg)	Hydrolyzable chlorine (%)	Colour (APHA, Gardner*)	Application	Description
	CHS-EPOXY® RR 300	40–90	2,90–3,30	max. 0,3	max.2*	Flexibilizer, low toxicity and vapour pressure, reduced reactivity, limited diluting power	Polypropyleneglycol diglycidyl ether
	CHS-EPOXY® RR 330	5–10	2,94–3,70	max. 0,1	max.1*	Low toxicity and vapour pressure, good diluting power, reduced reactivity	C12-C14 alkyl glycidyl ether
	CHS-EPOXY® RR 430	1–6	4,25–4,55	max. 0,05	max.1*	Low toxicity and vapour pressure, good diluting power, reduced reactivity	C8-C10 alkyl glycidyl ether
	CHS-EPOXY® RR 690	130–200	7,20–7,70	max. 0,1	max.1*	Excellent mechanical strength and reactivity, hot water and solvent resistance, limited diluting power	Trimethylol propane triglycidyl ether
	CHS-EPOXY® RR 700	15–25	6,70–7,20	max. 0,2	max.1*	Excellent reactivity at low temperatures and good solvent resistance, high mechanical strength, limited acid resistance	1, 6-hexanediol diglycidyl ether
	CHS-EPOXY® RR 800	10–25	7,60–8,10	max. 0,2	max.1*	Excellent reactivity at low temperatures and good solvent resistance, high mechanical strength, limited acid resistance	1, 4-butanediol diglycidyl ether

SPECIAL ADDITIVES – DECIDOL®

Under the trade name DECIDOL® we offer a range of acetyl alcohol-based surfactants ideally suited as a wetting agent and defoamer. These products fundamentally reduce surface tension, improve the wetting of surfaces, including hydrophobic substrates, regulate the formation of foam and help to stabilize the viscosity of the paint. The additives are non-toxic, silicone-free and fully compliant with REACH regulations.

DECIDOL® is available as a highly pure product or as solutions in different concentrations of solvents such as monoethylene glycol (MEG) and propylene glycol (PG), which we are able to produce according to customer requirements.



Product	Colour (APHA)	Concentration of H ₂ O (%)	TMDD Content (%)	MIBK Content (%)	HIOL Content (%)	Description
---------	---------------	---------------------------------------	------------------	------------------	------------------	-------------

DECIDOL®

DECIDOL®	150	max. 1	min. 98	max. 0,25	max. 0,45	White solid substance with menthol odour.
----------	-----	--------	---------	-----------	-----------	---

Product	Colour (Gardner)	Concentration of H ₂ O (%)	Density at 20 °C (kg/m³)	Description
---------	------------------	---------------------------------------	--------------------------	-------------

DECIDOL® Blends

DECIDOL® 105 MEG	4	max. 0,7	980–1 010	Colorless to light yellow, transparent liquid, slightly soluble in water, containing 50 % TMDD and 50 % MEG (Monoethylene glycol).
DECIDOL® 107 MEG	4	max. 0,7	945–965	Colorless to light yellow, transparent liquid, slightly soluble in water, containing 75 % TMDD and 25 % MEG (Monoethylene glycol).
DECIDOL® 105 PG	4	max. 0,7	955–975	Colorless to light yellow, transparent liquid, slightly soluble in water, containing 50 % TMDD and 50 % PG (Propylene glycol).

ALKYD & ROSIN RESINS

We have over 70 years of tradition as a manufacturer of alkyd resins produced using fusion technology (aromatic free products). Our wide-ranging product portfolio includes long, medium, and short oil alkyds which are either waterborne (CHS-HYDROSPOL®), solventborne, high solid, or solvent-free (CHS-ALKYD®).

In addition to the standard assortment of solventborne alkyds, our portfolio includes the following types of sustainable and environmentally friendly alkyds:

- 🌱 **high BIO content up to 92%**
- 🔴 **solvent-free**
- 🟡 **high solid with low VOC**
- 💧 **waterborne**

Our R&D teams work hard on to develop products that add real value to your business. This effort has resulted in a portfolio of special tailor made alkyd resins with exceptional properties; these alkyd resins have proven high-performance properties while respecting aesthetic, protective, and application requirements.



Product	Oil length (%)	Type of Oil or FA	Solvent	Viscosity (Pa.s, 23 °C)	Non-volatile content (%)	Acid value (mg KOH/g)	Colour (I ₂ mg/100 cm ³)	Description
---------	----------------	-------------------	---------	-------------------------	--------------------------	-----------------------	---	-------------

BINDERS FOR INDUSTRIAL COATINGS

	CHS-ALKYD® F 261 X 60	26	Vegetable drying oil	X	2,0–3,0	59,0–61,0	max.8	max.5	Fast-drying universal alkyd, excellent corrosion protection and mechanical properties, high hardness, low yellowing
	CHS-ALKYD® AKS 261 X 60	26	Vegetable drying oil	X	1,0–3,0	58,0–62,0	max.10	max.7	Acrylated alkyd, super fast-drying, superior corrosion resistance, low yellowing, improved flexibility
🔥	CHS-ALKYD® AL 3964	28	Linoleic rich FA, DCO	BuGB	13,0–18,0 ⁸	69,0–71,0	38–42	max.8	Water reducible alkyd, primers, topcoats and one-layer coatings (air dry, force dry, baking with melamine resins)
🔥	CHS-ALKYD® AL 3220	32	Coconut	M	0,9–1,5 ⁹	74,0–76,0	max.10	max.10	Stoving alkyd resin, wood and metal low yellowing coatings
🔥	CHS-ALKYD® C 351 E 75	39	FA	E	3,5–4,5	73,5–76,5	max.7	max.10	Stoving alkyd resin, for baking or nitrocellulose coatings
🔥	CHS-ALKYD® C 351 X 60	39	FA	X	0,7–1,3	58,0–62,0	max.6	max.10	Stoving alkyd resin, for baking or nitrocellulose coatings.
	CHS-ALKYD® TU 341 X 60	34	TOFA, DFA	X	2,0–5,0	58,0–62,0	max.7	max.8	High performance anticorrosive coatings
	CHS-ALKYD® AL 3701	37	TOFA	X	1,9–2,5	59,0–61,0	13–18	max.30	Lift resistant primer (air dry, force dry, baking), anticorrosive and rust resistant coatings, topcoats and one-layer application, as putties and fillers. High hardness
	CHS-ALKYD® S 401 X 55	40	Vegetable drying oil	X	0,8–1,2	53,5–56,5	max.7	max.8	Economic primers and anticorrosive coatings
	CHS-ALKYD® S 401 X 60	40	Vegetable drying oil	X	2,0–4,0	58,5–61,5	max.7	max.7	Economic primers and anticorrosive coatings
NEW	CHS-ALKYD S 405 N 60	40	Vegetable drying oil	N	3,0–7,0	59,0–61,0	max.8	max.10	Binder for solventborne non-aromatic primers, anticorrosive coatings and enamels, especially for metal substrates.
NEW	CHS-ALKYD S 405 NN 55	40	Vegetable drying oil	NN	3,0–7,0	54,0–56,0	max.8	max.10	Binder for solventborne non-aromatic primers, anticorrosive coatings and enamels, especially for metal substrates.
	CHS-ALKYD® S 471 WX 55	47	Vegetable drying oil	WX	2,9–5,3	53,5–56,5	max.5	max.8	Economic primers and anticorrosive coatings, for fast overcoating primers
	CHS-ALKYD® S 471 X 60	47	Vegetable drying oil	X	0,8–1,7	58,0–62,0	max.6	max.8	Economic primers and anticorrosive coatings
NEW	CHS-ALKYD® S 475 X 70	47	Vegetable drying oil	X	2,0–5,5	68,0–72,0	max. 10	max.12	Anticorrosion primers with low VOC content
NEW	CHS-ALKYD® S 475 NN 65	47	Vegetable drying oil	NN	4,0–9,0	64,0–66,0	max. 10	max.15	Solventborne non-aromatic primers , anticorrosive coatings and one-layer coatings
	CHS-ALKYD® S 491 W 55	49	Vegetable drying oil	W	2,5–5,5	54,0–56,0	max.6	max.8	Economic primers and anticorrosive coatings
	CHS-ALKYD® TU 497 S 57	49	TOFA	S	1,5–4,0	55,5–58,5	max.4	max.8	Fast drying & corrosion resistant, weathering resistance and outstanding adhesion, primers & single-layer coatings for iron and light metals
	CHS-ALKYD® M 552 WX 60	55	Linseed	WX	0,45–0,95	58,5–61,5	max.7	max.15	Lift resistant alkyd modified by novolac rosin resin, improved adhesion and chemical resistance, anticorrosion primers
	CHS-ALKYD® SU 621 N 50	62	Vegetable drying oil	N	0,5–2,0	48,5–51,5	max.7	max.7	Fast-drying urethanised alkyd, aromatic content less than 1%
	CHS-ALKYD® S 622 X 70	62	Vegetable drying oil	X	2,0–3,0	68,0–72,0	max.7	max.10	For air-drying coatings, mainly enamels, lacquers and wood stains for indoor and outdoor application.
	CHS-ALKYD® SU 632 N 60	63	Vegetable drying oil	N	0,9–1,5	57,0–59,0	max.2	max.10	Fast drying, outstanding hardness and mar resistance, excellent mechanical properties and weather-resistance, wood & metal
	CHS-ALKYD® SU 632 NN 55	63	Vegetable drying oil	NN	0,8–1,6	55,0–57,0	max.2	max.10	Fast drying, outstanding hardness and mar resistance, excellent mechanical properties and weather-resistance, wood & metal, aromatic content less than 1%
	CHS-ALKYD® SU 671 W 60	67	Vegetable drying oil	W	2,0–4,0	58,0–62,0	max.1	max.8	Fast-drying urethanised alkyd for coatings with high hardness
🔥	CHS-ALKYD® AL 2460	72	Linseed	NN	0,2–0,4	69,0–71,0	32–40		Binder for foundry sand moulds














🔥 low VOC

Product Notes: **1** Viscosity of 70% solution in butylglycol/ 25°C, **2** Viscosity of 40% solution in butylglycol/25°C, **3** In a solution, **4** Recommended mixing ration with filler, **5** Viscosity at 25°C (Brookfield), **6** System (part A:B) has to be mixed with water in the recommended correct ration - see Application Sheet, **7** System (part A:B) can be filled with additional filler in the recommended correct ratio - see Application Sheet, **8** Viscosity (Pa.s, 25°C), **9** Viscosity (Pa.s, 20°C), **10** 50% Xylene solution, **11** In time of loading, **12** Depends on technology used, (pbw) parts by weight.




Product	Oil length (%)	Type of Oil or FA	Solvent	Viscosity (Pa.s, 23 °C)	Non-volatile content (%)	Acid value (mg KOH/g)	Colour (I ₂ mg/100 cm ³)	Description
BINDERS FOR DECORATIVE COATINGS								
CHS-ALKYD® F 261 X 60	26	Vegetable drying oil	X	2,0–3,0	59,0–61,0	max.8	max.5	Fast-drying universal alkyd, excellent corrosion protection and mechanical properties, high hardness, low yellowing
CHS-ALKYD® AKS 261 X 60	26	Vegetable drying oil	X	1,5–5,0	58,0–62,0	max.10	max.7	Acrylated and styrenated alkyd, super fast-drying, superior corrosion resistance, low yellowing, improved flexibility
CHS-ALKYD® S 401 X 55	40	Vegetable drying oil	X	0,8–1,2	53,5–56,5	max.7	max.8	Economic primers and anticorrosive coatings
CHS-ALKYD® S 401 X 60	40	Vegetable drying oil	X	2,0–4,0	58,5–61,5	max.7	max.7	Economic primers and anticorrosive coatings
NEW CHS-ALKYD® S 405 N 60	40	Vegetable drying oil	N	3,0-7,0	59,0-61,0	max.8	max.10	Binder for solventborne non-aromatic primers, anticorrosive coatings and enamels, especially for metal substrates.
NEW CHS-ALKYD® S 405 NN 55	40	Vegetable drying oil	NN	3,0-7,0	54,0-56,0	max.8	max.10	Binder for solventborne non-aromatic primers, anticorrosive coatings and enamels, especially for metal substrates.
CHS-ALKYD® S 471 WX 55	47	Vegetable drying oil	WX	2,9–5,3	53,5–56,5	max.5	max.8	Economic primers and anticorrosive coatings, for fast overcoating primers
CHS-ALKYD® S 471 X 60	47	Vegetable drying oil	X	0,8–1,7	58,0–62,0	max.6	max.8	Economic primers and anticorrosive coatings
NEW CHS-ALKYD® S 475 X 70	47	Vegetable drying oil	X	2,0–5,5	68,0–72,0	max. 10	max. 12	Anticorrosion primers with low VOC content
NEW CHS-ALKYD® S 475 NN 65	47	Vegetable drying oil	NN	4,0–9,0	64,0–66,0	max. 10	max. 15	Solventborne non-aromatic primers , anticorrosive coatings and one-layer coatings
CHS-ALKYD® S 491 W 55	49	Vegetable drying oil	W	2,5–5,5	54,0–56,0	max.6	max.8	Economic primers and anticorrosive coatings
NEW CHS-ALKYD® TU 497 S 57	49	TOFA	S	1,5–4,0	55,5–58,5	max.4	max.8	Fast drying & corrosion resistant, weathering resistance and outstanding adhesion, primers & single-layer coatings for iron and light metals
CHS-ALKYD® T 501 WX 55	50	TOFA	WX	1,2–2,0	53,5–56,5	max.8	max.7	Maleinised fast-drying alkyd
CHS-ALKYD® M 552 WX 60	55	Linseed	WX	0,45–0,95	58,5–61,5	max.7	max.15	Lift resistant alkyd modified by novolac rosin resin, improved adhesion and chemical resistance, anticorrosion primers
CHS-ALKYD® ST 551 NN 50	55	Vegetable drying oil	NN	THIXO-TROPIC	48,5–51,5	max.8	slight opacity	High thixotropy alkyd, aromatic content less than 1% , flash point over 61 °C, polyamide type
CHS-ALKYD® S 621 W 60	62	Vegetable drying oil	W	1,1–2,3	58,5–61,5	max.7	max.7	Outdoor durability, wood coatings
CHS-ALKYD® SU 621 N 50	62	Vegetable drying oil	N	0,5–2,0	48,5–51,5	max.7	max.7	Fast-drying urethanised alkyd, aromatic content less than 1%
CHS-ALKYD® S 622 N 60	62	Vegetable drying oil	N	3,7–4,7	58,5–61,5	max.7	max.7	Outdoor durability, universal, aromatic content less than 1%
CHS-ALKYD® S 622 X 70	62	Vegetable drying oil	X	2,0–3,0	68,0–72,0	max.7	max.10	For air-drying coatings, mainly enamels, lacquers and wood stains for indoor and outdoor application.
CHS-ALKYD® S 623 NN 50	62	Vegetable drying oil	NN	0,31–0,56	48,5–51,5	max.5	max.10	Alkyd resin for lacquers and wood stains, interior/exterior applications
CHS-ALKYD® S 623 NN 60	62	Vegetable drying oil	NN	2,5–6,5	60,0–62,0	max.7	max.10	Universal alkyd resin, aromatic content less than 1%
CHS-ALKYD® SU 632 N 60	63	Vegetable drying oil	N	0,9–1,5	57,0–59,0	max.2	max.10	Fast drying, outstanding hardness and mar resistance, excellent mechanical properties and weather-resistance, wood & metal
CHS-ALKYD® SU 632 NN 55	63	Vegetable drying oil	NN	0,8–1,6	55,0–57,0	max.2	max. 10	Fast drying, outstanding hardness and mar resistance, excellent mechanical properties and weather-resistance, wood & metal, aromatic content less than 1%

Product	Oil length (%)	Type of Oil or FA	Solvent	Viscosity (Pa.s, 23 °C)	Non-volatile content (%)	Acid value (mg KOH/g)	Colour (I ₂ mg/100 cm ³)	Description
---------	----------------	-------------------	---------	-------------------------	--------------------------	-----------------------	---	-------------



BINDERS FOR DECORATIVE COATINGS

	CHS-ALKYD® S 651 N 70	65	Vegetable drying oil	N	5,5–9,5	68,0–72,0	max. 7	max. 8	Air-drying enamels, lacquers and wood stains for outdoor application
	CHS-ALKYD® S 652 NN 70	65	Vegetable drying oil	NN	9,0–11,0	68,0–72,0	max.7	max.8	Outdoor durability, aromatic content less than 1% , flash point over 61 °C
	CHS-ALKYD® S 653 W 70	65	Vegetable drying oil	W	12,0–14,0	69,0–71,0	max.7	max.8	Air-drying high molecular weight alkyd with outdoor resistance in white spirit
	CHS-ALKYD® SU 671 W 60	67	Vegetable drying oil	W	2,0–4,0	58,0–62,0	max.1	max.8	Fast-drying urethanised alkyd for coatings with high hardness
	CHS-ALKYD® S 670 NN 75	67	Vegetable drying oil	NN	2,5–3,5	74,0–76,0	max.7	max.10	Soya bean oil fatty acids based alkyd, flash point over 61 °C, air drying top-coats for exterior, wood and metal surfaces
	CHS-ALKYD® SUR 735 NN 80	73	Vegetable drying oil	NN	6,5–8,5	78,5–81,5	max.4	max.10	High solid alkyd resin, fast-drying, good hardness, gloss retention and weather-resistance, wood & metal
NEW 	CHS-ALKYD® ST 790 NN 75	79	Vegetable drying oil	NN	SOFT THIXO-TROPIC GEL	74,0–76,0	max.25	slight opacity	Medium and long oil alkyd coatings with low VOC content especially for wood application
	CHS-ALKYD® AL 8000	80	Linoleic rich FA		1,5–3,0 ⁹	97,0–100	max.10	max.30	Solvent-free alkyd resin, low yellowing.
	CHS-ALKYD® SU 830 N 85	83	Vegetable drying oil	N	2,5–3,5	83,5–86,5	max.10	max.8	High solid urethanised alkyd, low VOC content and excelent drying, for production of woodstains coating and paints for wood treatment.
	CHS-ALKYD® TRI 841	84	TOFA, DCO		2,5–3,5	97,0–100	max.10	max.16	Solvent-free alkyd, fast-drying & outdoor durability, low yellowing.
	CHS-ALKYD® S 830	83	Vegetable drying oil		3,0–4,0	97,0–100	max.10	max.7	Solvent-free good drying alkyd, super flexible, improved UV stability, interior/exterior use and wood coatings
	CHS-ALKYD® TI 870	87	TOFA		2,2–3,2	97,0–100	max.8	max.15	Solvent-free alkyd, low yellowing, high bio content , wood coating.
	CHS-HYDROSPOL® D 870	87	TOFA	V	0,01–0,1	49,0–53,0	max.8	milky white	Solvent-free fast-drying waterborne alkyd, high bio content , improved UV stability, for wood applications
	CHS-ALKYD® LM 920	92	Linoleic rich FA		2,2–3,2	97,0–100	max.8	max.10	Solvent-free super-fast drying alkyd, high bio content , superflexible, excellent UV resistance, high hydrophobicity, optimal for exterior applications
NEW 	CHS-HYDROSPOL D 920	92	Linoleic rich FA	V	0,01–0,1	49,0–53,0	max 8	milky white	Solvent-free fast-drying waterborne alkyd, high bio content , excellent UV stability, for wood applications

BINDERS FOR ADHESIVES

	ABIESTER® 90					100	max.20		Ester based rosin resin, coatings, hot melt adhesives & printing inks
	ABIFEN® 125 D					100	max.25		Novolac resin modified with rosin, coatings, adhesives & tyres
	ABIMAL® 125					100	max.40	max.35 ¹⁰	Ester based rosin resin, coatings, printing inks, fast-drying, gloss, light durability & weather resistance

BINDERS FOR PRINTING INKS

	CHS-ALKYD® AL 6400	64	Linseed		62–82	100	4–15		Production of typographic inks
	CHS-ALKYD® AL 7310	75	Vegetable drying oil		38–48	100	4–10	max.25	Production of offset inks (heatset, sheet offset & metal inks)

 high BIO content  low VOC  waterborne  solvent-free

Product Notes: **1** Viscosity of 70% solution in butylglycol/ 25°C, **2** Viscosity of 40% solution in butylglycol/25°C, **3** In a solution, **4** Recommended mixing ration with filler, **5** Viscosity at 25°C (Brookfield), **6** System (part A:B) has to be mixed with water in the recommended correct ration - see Application Sheet, **7** System (part A:B) can be filled with additional filler in the recommended correct ratio - see Application Sheet, **8** Viscosity (Pa.s, 25°C), **9** Viscosity (Pa.s, 20°C), **10** 50% Xylene solution, **11** In time of loading, **12** Depends on technology used, (pbw) parts by weight.

HYDROXIDES

Product	Modification	Concentration of NaOH (%)	Na ₂ CO ₃ (%)	Chlorides Cl- (ppm)	Fe (ppm)	SO ₄ ²⁻ (ppm)	PO ₄ ³⁻ (ppm)	Heavy metals as Pb (ppm)	Description
---------	--------------	---------------------------	-------------------------------------	---------------------	----------	-------------------------------------	-------------------------------------	--------------------------	-------------

SODIUM HYDROXIDE

NaOH - LIQUID		> 48	< 0,5	< 50	< 5				Clear, colourless liquid
NaOH - PELLETS	Technical grade	> 98	< 1	< 200	< 20	< 100	< 20	< 20	White, strongly hygroscopic lenticular pellets that may have a bluish, yellowish or greyish tint, absorbing CO ₂ and moisture in the open air
NaOH - PELLETS	Semipure	> 98	< 1	< 80	< 15	< 40	< 20	< 20	White, strongly hygroscopic lenticular pellets that may have a bluish, yellowish or greyish tint, absorbing CO ₂ and moisture in the open air
NaOH - PELLETS	Pharma grade (BP, EP, USP)	> 98	< 0,5	< 200	< 10	< 200		< 20	White, strongly hygroscopic lenticular pellets, rapidly dissolving in water, absorbing CO ₂ and moisture in the open air
NaOH - PELLETS	p.a.	> 98,5	< 0,4	< 70	< 8	< 40	< 3	< 10	White, strongly hygroscopic lenticular pellets, rapidly dissolving in water, absorbing CO ₂ and moisture in the open air
NaOH - PELLETS	Pure	> 98	< 1	< 70	< 10	< 40	< 5	< 10	White, strongly hygroscopic lenticular pellets, rapidly dissolving in water, absorbing CO ₂ and moisture in the open air

POTASSIUM HYDROXIDE

KOH - LIQUID		45 ± 0,5	< 0,3	< 35	< 5	< 20			Clear, colourless liquid.
KOH - LIQUID		50 ± 0,5	< 0,3	< 35	< 5	< 20			Clear, colourless liquid.
KOH - FLAKES		> 90	< 0,65	< 70	< 30	< 40			White flakes that may have a grayish or bluish tint, absorbing moisture and CO ₂ in the open air
KOH - PELLETS	Semipure	> 85	< 0,6	< 70	< 5	< 40	< 5	< 5	White, strongly hygroscopic lenticular pellets, rapidly dissolving in water, absorbing moisture and CO ₂ in the open air
KOH - PELLETS	Pharma grade (BP, EP, USP)	> 85	< 2,0	< 200	< 10	< 200	< 100	< 10	White, strongly hygroscopic lenticular pellets, rapidly dissolving in water, absorbing moisture and CO ₂ in the open air
KOH - PELLETS	p.a.	> 86	< 0,5	< 70	< 3	< 40	< 1	< 5	White, strongly hygroscopic lenticular pellets, rapidly dissolving in water, absorbing moisture and CO ₂ in the open air
KOH - PELLETS	Pure	> 86	< 0,5	< 70	< 3	< 40	< 5	< 5	White, strongly hygroscopic lenticular pellets, rapidly dissolving in water, absorbing moisture and CO ₂ in the open air

CHLORINE PRODUCTS & OTHER

Product	Colour (APHA)	Concentration (%)	Concentration of H ₂ O (%)	1,5 Hexadiene (%)	Stabilizer (%)	Description
ALLYLCHLORIDE	< 50	> 99	< 0,01	< 0,3	0,015–0,025 ¹¹	Clear liquid of characteristic pungent odour, extremely flammable, UV sensitive (darkens).

Product	Colour (APHA)	Concentration (%)	Concentration of H ₂ O (%)	Description
EPICHLOROHYDRIN	< 10	> 99,8	< 0,02	Colourless volatile liquid with a characteristic irritating odour.

Product	Concentration (%)	Concentration of Fe (%)	Concentration of free Cl ₂ (%)	Concentration of SO ₄ ²⁻ (%)	Evaporation residue (%)	Chlorinated hydrocarbons (%)	Description
HYDROCHLORIC ACID	> 31	< 0,03	< 0,01	< 0,04	< 0,1	< 0,0025	Clear, colourless liquid with a yellowish tint and a characteristic pungent odour.

Product	Colour (APHA)	Concentration (%)	Concentration H ₂ O (mg/kg)	Stabilizer (%)	Distillation range 95% (°C)	Density at 20 °C (kg/m³)	Description
PERCHLOROETHYLENE	< 15	> 99,9	< 34	0,0006–0,002 ¹¹	119,5–121,5	1623	Colourless, water-clear liquid, ether-like odour.

Product	Concentration of active Cl ₂ (g/l)	Concentration of NaOH (g/l)	Concentration of Na ₂ CO ₃ (g/l)	Concentration of Fe (g/l)	Description
SODIUM HYPOCHLORITE	>140 (summer – 1.5.–30.9.) >150 (winter – 1.10.–30.4.)	< 12	< 20	< 0,01	Yellow-green to yellow-brown liquid. It decomposes spontaneously at light, in case of increased temperature and in contact with specific metals.

Product	Colour (APHA)	Concentration of H ₂ O (%)	Concentration of HF acidimetr. KOH (%)	Description
TRIETHYLAMINE TRIHYDROFLUORIDE (TEA)	0–200	> 1,0	22–27	Faintly yellow clear liquid.

Product Notes: **1** Viscosity of 70% solution in butylglycol/ 25°C, **2** Viscosity of 40% solution in butylglycol/25°C, **3** In a solution, **4** Recommended mixing ration with filler, **5** Viscosity at 25°C (Brookfield), **6** System (part A:B) has to be mixed with water in the recommended correct ration - see Application Sheet, **7** System (part A:B) can be filled with additional filler in the recommended correct ratio - see Application Sheet, **8** Viscosity (Pa.s, 25°C), **9** Viscosity (Pa.s, 20°C), **10** 50% Xylene solution, **11** In time of loading, **12** Depends on technology used, (pbw) parts by weight.

Registered Trade Marks

ABIESTER® ABIFEN® ABIMAL® ENVIPOXY® EPOSTYL® CHS-ALKYD® CHS-EPODUR® CHS-EPOXY® CHS-HYDROSPOL® DECIDOL® SADURIT® TELALIT® VEROBOND®



Revoluční 1930/86, 400 32 Ústí nad Labem
Czech Republic
info@spolchemie.cz

www.spolchemie.com

2024_05

The information provided, as well as the recommendations relating to the application and final use of Spolchemie products, are given in good faith based on Spolchemie's current knowledge and experience of the products when properly stored, handled, and applied under normal conditions. In practice, the differences in the material and actual conditions are such that no warranty with respect to merchantability or suitability for a particular purpose, nor any liability arising out of any legal relationship whatsoever, may be inferred from this information, from any written recommendations, or from any other advice offered. Users should always refer to the most current issue of the technical and application data sheet for the product concerned. Copies are available at www.spolchemie.com.